Product Information

TROGAMID® Care MX97

MICROCRYSTALLINE AND TRANSPARENT POLYAMIDES FOR FOR MEDICAL APPLICATION



TROGAMID® Care MX is the material of choice for all applications dealing with pharmaceutical formulations, lipids or aggressive disinfectants, since it exhibits an exceptional resistance towards chemicals and stress-cracking. Examples include fluid and drug delivery equipment such as stop-cocks, dialyzer parts, housings, covers or hearing aids.

Target areas of application for TROGAMID® Care MX compounds include fluid and drug delivery systems, surgical instruments, housings, monitoring and imaging devices and durable medical equipment.

All advantages at a glance:
- High transparency
- High chemical resistance
- Very good stress crack resistance
- UV resistance
- High dynamic load-bearing capacity
- High impact resistance
- Easy processability & colorability
- Free of BPA
- Gamma and EtO sterilizable

Biocompatibility of TROGAMID® Care

Biocompatiblity was tested following ISO10993-1 recommendations for a surface medical device with up to 30 days body contact.

The material fulfills the requirements of USP<88> class VI.

Tests were performed by independent, certified laboratories.

Biocompatibility tests for TROGAMID® Care:

Processing of TROGAMID® Care

For information about processing of TROGAMID®, please follow the general recommendations about "Processing of TROGAMID® compounds".

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Key Features

Industrial Sector
Medical Devices

Processing
Injection molding, Extrusion

Delivery form
Pellets, Granules

Optics
Transparent

Resistance to
UV / light / weathering

Conformity
Food contact, Biocompatibility, Medical application

Additives
Release agent, Unfilled

Mechanical properties ISO	dry / cond	Unit	Test Standard
Tensile modulus	**1400 / -**	MPa	ISO 527
Tensile strength	**60 / -**	MPa	ISO 527
Yield stress	**60 / -**	MPa	ISO 527
Yield strain	**8 / -**	%	ISO 527
Stress at 50% strain	**42 / -**	MPa	ISO 527
Stress at break	**65 / -**	MPa	ISO 527
Nominal strain at break, tB	**>50 / -**	%	ISO 527
Charpy impact strength, +23°C	**N / -**	kJ/m²	ISO 179/1eU
Charpy impact strength, 0°C	**N / -**	kJ/m²	ISO 179/1eU
Charpy impact strength, -30°C	**N / -**	kJ/m²	ISO 179/1eU
Charpy notched impact strength, +23°C	**14 / 10.5**	kJ/m²	ISO 179/1eA
Type of failure	**C / C**	-	-
Charpy notched impact strength, 0°C	**14 / -**	kJ/m²	ISO 179/1eA
Type of failure	**C / -**	-	-
Charpy notched impact strength, -30°C	**13 / -**	kJ/m²	ISO 179/1eA
Type of failure	**C / -**	-	-
Flexural modulus, 23°C	**1700 / -**	MPa	ISO 178
Flexural stress at conv. deflection, 23°C	**50 / -**	MPa	ISO 178
Flexural strength, 23°C	**90 / -**	MPa	ISO 178

Flexural strain at flexural strength, 23°C	**9 / -**	%	ISO 178
Flexural strain at break, 23°C	**N / -**	%	ISO 178

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	**250 / ***	°C	ISO 11357-1/-3
Glass transition temperature, DSC	**140 / ***	°C	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	**108 / ***	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	**122 / ***	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	**135 / ***	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	**130 / ***	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	**90 / ***	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, 23°C to 55 °C, normal	**90 / ***	E-6/K	ISO 11359-1/-2
Melting Temperature	**250**	°C	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	**1020 / -**	kg/m³	ISO 1183
Water absorption	**3.5 / ***	%	Sim. to ISO 62
Humidity absorption	**1.5 / ***	%	Sim. to ISO 62
Shore D hardness	**81**[b] **/ -**	-	ISO 7619-1
Density	**1020**	kg/m³	ASTM D 792

b: 3 seconds

Burning Behav.	dry / cond	Unit	Test Standard
Burning behav. at 1.5 mm nom. thickn.	**HB / ***	class	IEC 60695-11-10
Thickness tested	**1.6 / ***	mm	-
Burning behav. at thickness h	**HB / ***	class	IEC 60695-11-10
Thickness tested	**0.8 / ***	mm	-

Electrical properties	dry / cond	Unit	Test Standard
Relative permittivity, 100Hz	**3.6 / -**	-	IEC 62631-2-1
Relative permittivity, 1MHz	**3.2 / -**	-	IEC 62631-2-1
Dissipation factor, 100Hz	**120 / -**	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	**325 / -**	E-4	IEC 62631-2-1
Dielectric strength, AC, S20/P50	**27 / -**	kV/mm	Sim. to IEC 60243-1
CTI, test solution A, 50 drops value	**600 / -**	-	IEC 60112
Assessment of the insulation group	**I**	-	DIN EN 60664-1

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	**31 / ***	cm^3/10min	ISO 1133
Temperature	**285 / ***	°C	-
Load	**5 / ***	kg	-
Molding shrinkage, parallel	**0.7 / ***	%	ISO 294-4, 2577
Molding shrinkage, normal	**0.8 / ***	%	ISO 294-4, 2577

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	**280**	°C	ISO 294
Injection Molding, mold temperature	**80**	°C	ISO 294
Injection Molding, injection velocity	**200**	mm/s	ISO 294

Characteristics

Processing
Film extrusion, Profile extrusion, Sheet extrusion

Special Characteristics
Halogen-free, Semi-crystalline, Environmental stress crack resistance, U.V. stabilized

Regulatory
US Pharmacopeia Class VI conformity

Additives
Release agent, Processing aids

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

® is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com

www.plastics-database.com

Leading Beyond Chemistry