Product Information

TROGAMID® myCX high flow

MICROCRYSTALLINE, PERMANENTLY TRANSPARENT POLYAMIDE

TROGAMID® myCX high flow is a microcrystalline transparent polyamide for the manufacture of parts in the optical industry, like lenses according the injection molding procedure.

TROGAMID® myCX high flow is supplied as spherical pellets in moisture-proof packaging.

Pigmentation may affect values.

For information about processing of TROGAMID®, please follow the general commendations about "Processing of TROGAMID® compounds".

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.TROGAMID.COM

Key Features

Industrial Sector
Optics, Sports and Lifestyle

Processing
Injection molding, Extrusion

Optics
Transparent, High gloss, X-ray transparent

Resistance to
Heat (thermal stability), Hydrolysis / hot water, UV / light / weathering, Fatigue resistance

Conformity
Food contact

Additives
Unfilled

LCA-values	dry	Unit	Test Standard
LCA name of certificate	TROGAMID® microcrystalline	-	ISO 14040, 14044
LCA certifier	TÜV Rheinland	-	ISO 14040, 14044
Blue water consumption	**13.1**	kg	ISO 14040, 14044
Global Warming Potential incl. bio. C incl. LUC	**7.7**	kg CO_2 eq./kg	ISO 14040, 14044
Global Warming Potential excl. bio. C incl. LUC	**7.7**	kg CO_2 eq./kg	ISO 14040, 14044
Land use (ReCiPe 2016)	**0**	Annual crop eq. y	ISO 14040, 14044

EVONIK Leading Beyond Chemistry

Mechanical properties ISO	dry / cond	Unit	Test Standard
Tensile modulus	**1480 / 1490**	MPa	ISO 527
Tensile strength	**59 / 63**	MPa	ISO 527
Yield stress	**59 / 63**	MPa	ISO 527
Yield strain	**8 / 7**	%	ISO 527
Stress at 50% strain	**42 / 39**	MPa	ISO 527
Stress at break	**65 / 60**	MPa	ISO 527
Nominal strain at break, εtB	**180 / 185**	%	ISO 527
Charpy impact strength, +23°C	**N / N**	kJ/m²	ISO 179/1eU
Charpy impact strength, -30°C	**N / N**	kJ/m²	ISO 179/1eU
Charpy notched impact strength, +23°C	**11 / 12**	kJ/m²	ISO 179/1eA
Type of failure	**C / C**	-	-
Charpy notched impact strength, -30°C	**11 / 12**	kJ/m²	ISO 179/1eA
Type of failure	**C / C**	-	-
Flexural modulus, 23°C	**1460 / 1500**	MPa	ISO 178
Flexural stress at conv. deflection, 23°C	**52 / 54**	MPa	ISO 178
Flexural strength, 23°C	**81 / 88**	MPa	ISO 178
Flexural strain at flexural strength, 23°C	**8 / 8**	%	ISO 178
Flexural stress at break, 23°C	**N / N**	MPa	ISO 178
Flexural strain at break, 23°C	**N / N**	%	ISO 178

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	**247 / ***	°C	ISO 11357-1/-3
Glass transition temperature, DSC	**135 / ***	°C	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	**102 / ***	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	**120 / ***	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	**133 / ***	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	**127 / ***	°C	ISO 306

Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	**92 / ***	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, 23°C to 55 °C, normal	**96 / ***	E-6/K	ISO 11359-1/-2
Melting Temperature	**247**	°C	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	**1020 / -**	kg/m³	ISO 1183
Water absorption	**3 / ***	%	Sim. to ISO 62
Humidity absorption	**2 / ***	%	Sim. to ISO 62
Shore D hardness	**81**[b] **/ -**	-	ISO 7619-1
Density	**1020**	kg/m³	ASTM D 792

b: 3 seconds

Optical properties	dry	Unit	Test Standard
Haze	**2.1**	%	ASTM D 1003
Haze Thickness tested	**2**	mm	-
Light Transmittance	**92**	%	ASTM D 1003
Light Transmittance Thickness tested	**2**	mm	ASTM D 1003

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	**11 / ***	cm³/10min	ISO 1133
Temperature	**280 / ***	°C	-
Load	**2.16 / ***	kg	-
Molding shrinkage, parallel	**0.7 / ***	%	ISO 294-4, 2577
Molding shrinkage, normal	**0.7 / ***	%	ISO 294-4, 2577
Mold temperature	**80 / ***	°C	-
Melt temperature	**280 / ***	°C	-
Flow length, flow spiral	**295**	mm	Evonik standard
Flow cross section	**6 x 2**	mm²	Evonik standard
Mold temperature, flow spiral	**80**	°C	Evonik standard

Melt temperature, flow spiral	**280**	°C	Evonik standard
Injection pressure, flow spiral	**1000**	bar	Evonik standard
Flow length, flow spiral	**464**	mm	Evonik standard
Flow cross section	**6 x 2**	mm^2	Evonik standard
Mold temperature, flow spiral	**80**	°C	Evonik standard
Melt temperature, flow spiral	**300**	°C	Evonik standard
Injection pressure, flow spiral	**1000**	bar	Evonik standard

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	**280**	°C	ISO 294
Injection Molding, mold temperature	**80**	°C	ISO 294
Injection Molding, injection velocity	**200**	mm/s	ISO 294

Characteristics

Applications
Fiber optic cable, (Sun-) glasses, Hygiene and cosmetics, Lenses, Monofilament

Processing
Film extrusion

Special Characteristics
Halogen-free, Phosphorus-free, High impact strength, Low viscosity

Features
optical UV-protection, Weldable, Low birefringence, Non-corrosive, Dishwasher detergents resistant

Regulatory
Food contact 10/2011/EC

Color
Natural color

Delivery form
Spherical pellets

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

® is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com

www.plastics-database.com