Product Information

VESTAKEEP® 2000 CF30

CARBON FIBER-REINFORCED, MEDIUM VISCOSITY POLYETHER ETHER KETONE



VESTAKEEP® 2000 CF30 is a medium-viscosity, carbon fiber-reinforced (30%) polyether ether ketone for injection molding.

The semi-crystalline polymer features superior, mechanical, thermal and chemical resistance. Parts made from VESTAKEEP® 2000 CF30 are of low flammability.

VESTAKEEP® 2000 CF30 can be processed by common injection machines for thermoplastics.

We recommend a melt temperature between 380°C and 400°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 2000 CF30 is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

Pigmention may effect values.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

For information about processing of VESTAKEEP® 2000 CF30, please follow the general recommendations in our brochure "VESTAKEEP® PEEK-Processing Guidelines".

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM OR VISIT OUR PRODUCT AT WWW.INDUSTRIAL.VESTAKEEP.COM

Mechanical properties ISO	dry	Unit	Test Standard
Tensile Modulus	**24000**	MPa	ISO 527
Tensile Strength	**251**	MPa	ISO 527
Stress at break	**251**	MPa	ISO 527
Strain at break, εB	**1.85**	%	ISO 527
Charpy impact strength, +23°C	**51**	kJ/m²	ISO 179/1eU
Type of failure	**C**	-	-
Charpy impact strength, -30°C	**45**	kJ/m²	ISO 179/1eU
Type of failure	**C**	-	-

Charpy notched impact strength, +23°C	**8**	kJ/m²	ISO 179/1eA
Type of failure	**C**	-	-
Charpy notched impact strength, -30°C	**8**	kJ/m²	ISO 179/1eA
Type of failure	**C**	-	-
Flexural modulus, 23°C	**21500**	MPa	ISO 178
Flexural stress at break, 23°C	**390**	MPa	ISO 178
Flexural strain at break, 23°C	**2.1**	%	ISO 178

Mechanical properties ASTM	**dry**	**Unit**	**Test Standard**
tensile modulus, annealed	**22752.7**	MPa	ASTM D 638
Stress at break, 23°C, annealed	**2**	%	ASTM D 638
Strain at break, 23°C, annealed	**248000**	Pa	ASTM D 638

Thermal properties	**dry**	**Unit**	**Test Standard**
Melting temperature	**340**	°C	ISO 11357-1/-3
Glass transition temperature	**146**	°C	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	**330**	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	**340**	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	**343**	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	**340**	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	**10**	E-6/K	ISO 11359-1/-2

Physical properties	**dry**	**Unit**	**Test Standard**
Water absorption	**0.4**	%	Sim. to ISO 62
Density	**1410**	kg/m³	ISO 1183

Burning Behav.	**dry**	**Unit**	**Test Standard**
YellowCard available	yes	-	-
Burning behav. at 1.5 mm nom. thickn.	**V-0**	class	IEC 60695-11-10


Thickness tested	**1.6**	mm	-
Yellow Card available	yes	-	-
Oxygen index	**47**	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
GWFI - thickness tested (1)	**2**	mm	-
Glow Wire Ignition Temperature (GWIT)	**875**	°C	IEC 60695-2-13
GWIT - thickness tested (1)	**2**	mm	-
Limiting Oxygen Index	**47**	%	ASTM D 2863

Electrical properties	**dry**	**Unit**	**Test Standard**
Relative permittivity, 1MHz	**17**	-	IEC 62631-2-1
Dissipation factor, 1MHz	**2300**	E-4	IEC 62631-2-1
Volume resistivity, pV	**10000**	Ohm*m	IEC 62631-3-1

Rheological properties	**dry**	**Unit**	**Test Standard**
Melt volume-flow rate, MVR	**19**	cm^3/10min	ISO 1133
Temperature	**400**	°C	-
Load	**5**	kg	-
Molding shrinkage, parallel	**0**	%	ISO 294-4, 2577
Molding shrinkage, normal	**0.4**	%	ISO 294-4, 2577
Mold temperature	**180**	°C	-
Melt temperature	**390**	°C	-

Diagrams

Stress-strain (anisotropy)



Characteristics

Key Feature, Industrial Sector
Aircraft and Aerospace, Electrical and Electronical, Instustry and Building Construction

Key Feature, Processing
Injection Molding

Key Feature, Resistance to
Fire / Burn

Special Characteristics
Heat-stabilized

Features
General Chemical Resistance

Color
Natural Color

Delivery form
Pellets, Granules, Cylindrical Pellets

Chemical Resistance
Aging resistance

Chemical Media Resistance

Acids

✔	Acetic Acid (5% by mass) (23°C)
✔	Citric Acid solution (10% by mass) (23°C)
✔	Hydrochloric Acid (36% by mass) (23°C)
✖	Nitric Acid (40% by mass) (23°C)
✔	Sulfuric Acid (5% by mass) (23°C)
✔	Chromic Acid solution (40% by mass) (23°C)

Bases

- ✔ Sodium Hydroxide solution (35% by mass) (23°C)
- ✔ Sodium Hydroxide solution (1% by mass) (23°C)
- ✔ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ✔ Isopropyl alcohol (23°C)
- ✔ Methanol (23°C)
- ✔ Ethanol (23°C)

Hydrocarbons

- ✔ n-Hexane (23°C)
- ✔ Toluene (23°C)
- ✔ iso-Octane (23°C)

Ketones

- ✔ Acetone (23°C)

Ethers

- ✔ Diethyl ether (23°C)

Mineral oils

- ✔ SAE 10W40 multigrade motor oil (23°C)
- ✔ Insulating Oil (23°C)

Standard Fuels

- ✔ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✔ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✔ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Salt solutions

- ✔ Sodium Chloride solution (10% by mass) (23°C)
- ✔ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✔ Sodium Carbonate solution (20% by mass) (23°C)
- ✔ Sodium Carbonate solution (2% by mass) (23°C)
- ✔ Zinc Chloride solution (50% by mass) (23°C)

Other

- ✔ Ethyl Acetate (23°C)

- ✔ Hydrogen peroxide (23°C)
- ✔ Ethylene Glycol (50% by mass) in water (108°C)
- ✔ Water (23°C)
- ✔ Deionized water (90°C)

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

® is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com

www.plastics-database.com