Product Information

VESTAKEEP® 2000 G BK

MEDIUM VISCOSITY, UNREINFORCED POLYETHER ETHER KETONE



VESTAKEEP® 2000 G BK is a medium viscosity, unreinforced polyether ether ketone for injection molding.

The semi-crystalline polymer features superior, thermal and chemical resistance. Parts made from VESTAKEEP® 2000 G BK are of low flammability.

VESTAKEEP® 2000 G BK can be processed by common machines for thermoplastics.

We recommend a melt temperature between 360°C and 380°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 2000 G BK is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

Pigmentation may affect values.

For information about processing VESTAKEEP® 2000 G BK, please follow the general recommendations in our brochure "VESTAKEEP® PEEK Processing Guidelines".

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM OR VISIT OUR PRODUCT AT WWW.INDUSTRIAL.VESTAKEEP.COM

Mechanical properties ISO	dry	Unit	Test Standard
Tensile Modulus	**3700**	MPa	ISO 527
Tensile Strength	**100**	MPa	ISO 527
Yield stress	**100**	MPa	ISO 527
Yield strain	**5**	%	ISO 527
Stress at break	**70**	MPa	ISO 527
Nominal strain at break, εtB	**20**	%	ISO 527
Charpy impact strength, +23°C	**N**	kJ/m^2	ISO 179/1eU
Charpy impact strength, -30°C	**N**	kJ/m^2	ISO 179/1eU

EVONIK Leading Beyond Chemistry

Charpy notched impact strength, +23°C	**5.5**	kJ/m²	ISO 179/1eA
Type of failure	**C**	-	-
Charpy notched impact strength, -30°C	**5.5**	kJ/m²	ISO 179/1eA
Type of failure	**C**	-	-
Flexural modulus, 23°C	**3600**	MPa	ISO 178
Flexural stress at conv. deflection, 23°C	**120**	MPa	ISO 178
Flexural strain at flexural strength, 23°C	**7**	%	ISO 178
Flexural stress at break, 23°C	**N**	MPa	ISO 178
Flexural strain at break, 23°C	**N**	%	ISO 178

Thermal properties	**dry**	**Unit**	**Test Standard**
Temp. of deflection under load A, 1.80 MPa	**156**	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	**204**	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	**335**	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	**310**	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	**60**	E-6/K	ISO 11359-1/-2

Physical properties	**dry**	**Unit**	**Test Standard**
Density	**1300**	kg/m³	ISO 1183

Burning Behav.	**dry**	**Unit**	**Test Standard**
Burnin behav. at thickness h	**V-0**	class	IEC 60695-11-10
Thickness tested	**3.2**	mm	-

Rheological properties	**dry**	**Unit**	**Test Standard**
Melt volume-flow rate, MVR	**70**	cm³/10min	ISO 1133
Temperature	**380**	°C	-
Load	**5**	kg	-
Molding shrinkage, parallel	**1.1**	%	ISO 294-4, 2577

Molding shrinkage, normal	**1.1**	%	ISO 294-4, 2577

Characteristics

Key Feature, Industrial Sector
Automotive, Instustry and Building Construction

Key Feature, Processing
Injection Molding, Extrusion

Key Feature, Resistance to
Fire / Burn

Key Feature, Certificate / Licence
Food contact

Applications
Encapsulation

Special Characteristics
Heat-stabilized

Color
Black

Delivery form
Pellets, Granules

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

® is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com

www.plastics-database.com