Product Information

VESTAKEEP® 4000 CFL30

CARBON FIBER-REINFORCED, HIGH VISCOSITY POLYETHER ETHER KETONE



VESTAKEEP® 4000 CFL30 is a carbon fiber reinforced polyether ether ketone for injection molding.

The semi-crystalline polymer features superior mechanical, thermal, and chemical resistance. Parts made from VESTAKEEP® 4000 CFL30 are characterized by low flammability.

VESTAKEEP® 4000 CFL30 can be processed by common injection molding machines for thermoplastics.

We recommend a melt temperature between 380°C and 400°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 4000 CFL30 is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Pigmentation may affect values.

For information about processing VESTAKEEP® 4000 CFL30, please follow the general recommendations in our brochure "VESTAKEEP® PEEK Processing Guidelines."

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM OR VISIT OUR PRODUCT AT WWW.INDUSTRIAL.VESTAKEEP.COM

Mechanical properties ISO	dry	Unit	Test Standard
Tensile Modulus	**24000**	MPa	ISO 527
Tensile Strength	**245**	MPa	ISO 527
Stress at break	**245**	MPa	ISO 527
Strain at break, εB	**2**	%	ISO 527
Charpy notched impact strength, +23°C	**11**	kJ/m²	ISO 179/1eA
Type of failure	**C**	-	-

Mechanical properties ASTM	dry	Unit	Test Standard
tensile modulus, annealed	**24131.6**	MPa	ASTM D 638

EVONIK Leading Beyond Chemistry

Stress at break, 23°C, annealed	**2**	%	ASTM D 638
Strain at break, 23°C, annealed	**265000**	Pa	ASTM D 638
Flexural Modulus	**2120**	MPa	ASTM D 790
Flexural Strength	**400**	MPa	ASTM D 790

Physical properties	**dry**	**Unit**	**Test Standard**
Density	**1400**	kg/m^3	ISO 1183
Shore D hardness, 1s, annealed	**92**	-	ASTM D 2240

Rheological properties	**dry**	**Unit**	**Test Standard**
Melt volume-flow rate, MVR	**24**	$cm^3/10min$	ISO 1133
Temperature	**400**	°C	-
Load	**21.6**	kg	-

Polymer analytics	**dry**	**Unit**	**Test Standard**
Moisture content	**0.15**	Gew.-%	ISO 15512

Characteristics

Key Feature, Industrial Sector
Oil and Gas

Key Feature, Processing
Injection Molding

Applications
Encapsulation

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

® is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com

www.plastics-database.com