Product Information

VESTAKEEP® 4000 GF30 BK

GLASS FIBER-REINFORCED (30%) POLYETHER ETHER KETONE



VESTAKEEP® 4000 GF30 BK is a glass fiber-reinforced (30%) polyether ether ketone for injection molding.

The semi-crystalline polymer features superior mechanical, thermal, and chemical resistance. Parts made from VESTAKEEP® 4000 GF30 BK are of low flammability.

VESTAKEEP® 4000 GF30 BK can be processed on common injection molding machines for thermoplastics.

We recommend a melt temperature of 380°C to 400°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 4000 GF30 BK is supplied as cylindrical pellets in 25 kg boxes with moisture-proof polyethylene liners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Pigmentation may affect the values.

For guidance processing of VESTAKEEP® 4000 GF30 please follow the general recommendations in our brochure "VESTAKEEP® PEEK Processing Guidelines".

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM OR VISIT OUR PRODUCT AT WWW.INDUSTRIAL.VESTAKEEP.COM

Mechanical properties ISO	dry	Unit	Test Standard
Tensile Modulus	**11000**	MPa	ISO 527
Tensile Strength	**160**	MPa	ISO 527
Stress at break	**160**	MPa	ISO 527
Strain at break, εB	**2**	%	ISO 527
Charpy impact strength, +23°C	**70**	kJ/m²	ISO 179/1eU
Type of failure	**C**	-	-
Charpy impact strength, -30°C	**75**	kJ/m²	ISO 179/1eU
Type of failure	**C**	-	-

EVONIK Leading Beyond Chemistry

Charpy notched impact strength, +23°C	**10**	kJ/m²	ISO 179/1eA
Type of failure	**C**	-	-
Charpy notched impact strength, -30°C	**9**	kJ/m²	ISO 179/1eA
Type of failure	**C**	-	-

Thermal properties	**dry**	**Unit**	**Test Standard**
Melting temperature	**340**	°C	ISO 11357-1/-3
Temp. of deflection under load A, 1.80 MPa	**312**	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	**335**	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	**340**	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	**335**	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	**30**	E-6/K	ISO 11359-1/-2

Physical properties	**dry**	**Unit**	**Test Standard**
Density	**1500**	kg/m³	ISO 1183

Burning Behav.	**dry**	**Unit**	**Test Standard**
Burnin behav. at thickness h	**V-0**	class	IEC 60695-11-10
Thickness tested	**3.2**	mm	-
Burning behav. at 1.5 mm nom. thickn.	**V-0**	class	IEC 60695-11-10
Thickness tested	**1.6**	mm	-
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	**825**	°C	IEC 60695-2-13

Electrical properties	**dry**	**Unit**	**Test Standard**
Relative permittivity, 1MHz	**3.3**	-	IEC 62631-2-1
Volume resistivity, ρV	**1E13**	Ohm*m	IEC 62631-3-1
Surface resistance, RSD	**1E14**	Ohm	IEC 62631-3-2
CTI, test solution A, 50 drops value	**200**	-	IEC 60112

Rheological properties	dry	Unit	Test Standard
Melt volume-flow rate, MVR	**32**	cm^3/10min	ISO 1133
Temperature	**400**	°C	-
Load	**21.6**	kg	-
Melt volume-flow rate, MVR	**32.9**	cm^3/10min	ISO 1133
Temperature	**400**	°C	-
Load	**21.6**	kg	-
Molding shrinkage, parallel	**0.3**	%	ISO 294-4, 2577
Molding shrinkage, normal	**0.6**	%	ISO 294-4, 2577
Mold temperature	**180**	°C	-

Polymer analytics	dry	Unit	Test Standard
Moisture content	**0.04**	Gew.-%	ISO 15512

Characteristics

Key Feature, Industrial Sector
Automotive, Instustry and Building Construction

Key Feature, Processing
Injection Molding, Extrusion

Key Feature, Resistance to
Heat (Thermal Stability), Fire / Burn

Key Feature, Additives
Glass fibre

Applications
Encapsulation

Special Characteristics
Semi-crystalline, Low Warpage / Low Shrinkage

Features
General Chemical Resistance

Color
Black

Delivery form
Pellets, Granules

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

® is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com

www.plastics-database.com